

One (1) piece of submitted sample said to be non-metal penetration resistant insert.Test Method:SATRA TM240: 2001Ref. No.:20150612Ref.:WELLMAX ANTI-PENETRATION MID SOLEDate Received/Date Test Started:Jun. 12, 2015Date Final Information Confirmed:Jul. 02, 2015

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By: For Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

Huang Ning, Andy Assistant General Manager



Page 1 Of 3

Intertek Testing Services Shenzhen Limited, Guangzhou Branch Block E, No.7-2, Caipin Road, Guangzhou Science City, Getdd Guangzhou. 深圳天祥质量技术服务有限公司广州分公司 广州经济技术开发区科学城彩频路 7 号之二E 栋 Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

wx / tiffanydeng



Number: GZHT90525859

Electrical Resistance Of Footwear Components (SATRA TM240: 2001, Dry: 20°C, 30% R.H. For 7 Days, Wet: 20

℃, 85% R.H. For 7 Days)

Dry	$< 1 \times 10^{3} \Omega$
Wet	$< 1 \times 10^{3} \Omega$

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

wx / tiffanydeng

Intertek Testing Services Shenzhen Limited, Guangzhou Branch Block E, No.7-2, Caipin Road, Guangzhou Science City, Getdd Guangzhou. 深圳天祥质量技术服务有限公司广州分公司 广州经济技术开发区科学城彩频路 7 号之二E 栋 Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663 Page 2 Of 3



Number: GZHT90525859



wx / tiffanydeng

Intertek Testing Services Shenzhen Limited, Guangzhou Branch Block E, No.7-2, Caipin Road, Guangzhou Science City, Getdd Guangzhou. 深圳天祥质量技术服务有限公司广州分公司 广州经济技术开发区科学城彩频路 7 号之二 E 栋 Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663 Page 3 Of 3